



中国认可  
检测  
TESTING  
CNAS L5526



# TEST REPORT

NSF (Shanghai) Testing Technology Co., Ltd.  
Unit D/F, 1 Floor, Building 10, 1188 Lianhang Road,  
Minhang District, Shanghai, China  
Tel: +86.21.2428.6300 | Fax: +21.2428.6299  
www.nsfchinalab.org

**Send To: C0312750**

**Facility: C0312751**

CPI CIXI CIPSA CO., LTD.  
European Industrial Park A Zone A3-10-4, First Binhai  
Road, Num 389, Hangzhou Bay New Zone Cixi  
Economic Develop Zone, Cixi City, Zhejiang, China

CPI CIXI CIPSA CO., LTD.  
European Industrial Park A Zone A3-10-4, First Binhai  
Road, Num 389, Hangzhou Bay New Zone Cixi Economic  
Develop Zone, Cixi City, Zhejiang, China

**Result Complete**

**Report Date 08-Dec-2016**

Customer Name CPI CIXI CIPSA CO., LTD.  
Description Rubber Material Pieces  
Model Name CPI-1EPDM70FDA0001.DS EPDM 70SH FDA  
Product material EPDM  
Country of Destination USA  
Test Type Test Only  
Job Number J-00244559  
Sample Reception Date 01-Dec-2016  
Testing Date 01-Dec-2016~07-Dec-2016

## Summary of Results

| Testing Parameters and Standards  | Result     |
|---|------------|
| Determination of extractive residue according to US FDA 21 CFR 177.2600 | See page 2 |

## Report Authorization

*Lucy Shu*



Lucy Shu- Laboratory QA Manager  
NSF (Shanghai) Testing Technology Co., Ltd.

**Date 08-Dec-2016**

FI20161208003524

J-00244559

Page 1 / 3

The reports will set forth in writing the findings of NSF solely with respect to the products identified therein and, unless specifically and expressly indicated in the reports, the results set forth in such reports will not be indicative or representative of the characteristics of the lot from which a product may be taken. Improper use for publicity purposes using the test result (s) is prohibited except with the specific written authorization of NSF. This report shall not be reproduced, except in its entirety, without the written approval of NSF. This report does not represent NSF Certification or authorization to use the NSF Mark. Authorization to use the NSF Mark is limited to products appearing in the Company's Official NSF Listing ([www.nsf.org](http://www.nsf.org)). The results relate only to those items tested, in the condition received at the laboratory

1. **Determination of extractives residue according to US FDA 21 CFR 177.2600**

1.1 Testing procedure:

Extract samples with the extractive solvents at the indicated extractive conditions (water at reflux temperature for initial 7h and later 2h, n-hexane at reflux temperature for initial 7h and later 2h), weigh the residue and calculate total extractives in mg per square inch of the sample extracted.

1.2 Testing result:

| Sample No.   | Testing Parameter                   |            | Unit               | Result  | Acceptance | Conclusion |
|--------------|-------------------------------------|------------|--------------------|---------|------------|------------|
| S-0001317842 | *Extractives residue<br>( Water )   | Initial 7h | mg/in <sup>2</sup> | ND(1.0) | 20         | Pass       |
|              |                                     | Later 2h   | mg/in <sup>2</sup> | ND(0.1) | 1          | Pass       |
|              | Extractives residue<br>( n-hexane ) | Initial 7h | mg/in <sup>2</sup> | 18      | 175        | Pass       |
|              |                                     | Later 2h   | mg/in <sup>2</sup> | 0.6     | 4          | Pass       |

Remark

- 1) ND=Not Detected, less than reporting limit.
- 2) The result of S-0001317842 Extractives residue in water are copies of S-0001302783 in J-00231080.



Picture of sample



Tested Sample

End of Report

