



中国认可
检测
TESTING
CNAS L5526



TEST REPORT

NSF (Shanghai) Testing Technology Co., Ltd.
Unit D/F, 1 Floor, Building 10, 1188 Lianhang Road,
Minhang District, Shanghai, China
Tel: +86.21.2428.6300 | Fax: +21.2428.6299
www.nsfchinalab.org

Send To: C0312750

Facility: C0312751

CPI CIXI CIPSA CO., LTD.
European Industrial Park A Zone A3-10-4, First
Binhai Road, Num 389, Hangzhou Bay New Zone
Cixi Economic Develop Zone, Cixi City, Zhejiang, China

CPI CIXI CIPSA CO., LTD.
European Industrial Park A Zone A3-10-4, First Binhai
Road, Num 389, Hangzhou Bay New Zone Cixi
Economic Develop Zone, Cixi City, Zhejiang, China

Result Complete

Report Date 06-Dec-2016

Customer Name CPI CIXI CIPSA CO., LTD.
Description Rubber Material Pieces
Model Name CPI-1FKM70FDA0001.DS FKM 70SH FDA
Product material FKM
Country of Destination USA
Test Type Test Only
Job Number J-00231081
Sample Reception Date 08-Oct-2016
Testing Date 08-Oct-2016~11-Oct-2016

Summary of Results

Testing Parameters and Standards	Result
Determination of extractive residue according to US FDA 21 CFR 177.2600	See page 2

This report replaces the previously issued report # F120161014051625.

Report Authorization

Lucy Shu



Lucy Shu- Laboratory QA Manager
NSF (Shanghai) Testing Technology Co., Ltd.

Date 06-Dec-2016

F120161206032610

J-00231081

Page 1 / 3

The reports will set forth in writing the findings of NSF solely with respect to the products identified therein and, unless specifically and expressly indicated in the reports, the results set forth in such reports will not be indicative or representative of the characteristics of the lot from which a product may be taken. Improper use for publicity purposes using the test result (s) is prohibited except with the specific written authorization of NSF. This report shall not be reproduced, except in its entirety, without the written approval of NSF. This report does not represent NSF Certification or authorization to use the NSF Mark. Authorization to use the NSF Mark is limited to products appearing in the Company's Official NSF Listing (www.nsf.org). The results relate only to those items tested, in the condition received at the laboratory

1. **Determination of extractives residue according to US FDA 21 CFR 177.2600**

1.1 Testing procedure:

Extract samples with the extractive solvents at the indicated extractive conditions (water at reflux temperature for initial 7h and later 2h, n-hexane at reflux temperature for initial 7h and later 2h), weigh the residue and calculate total extractives in mg per square inch of the sample extracted.

1.2 Testing result:


Sample No.	Testing Parameter		Unit	Result	Acceptance	Conclusion
S-0001302784	Extractives residue (Water)	Initial 7h	mg/in ²	ND(1.0)	20	Pass
		Later 2h	mg/in ²	ND(0.1)	1	Pass
	Extractives residue (n-hexane)	Initial 7h	mg/in ²	12	175	Pass
		Later 2h	mg/in ²	2.9	4	Pass

Remark

ND=Not Detected, less than reporting limit.



Picture of sample



End of Report

